

Umka Special GT2

Technical Specification

Tehnička Specifikacija



Grammage / Gramatura	Thickness / Debljina	Stiffness / Krutost LW5 ⁰	
		md	cd
g/m ²	µm	mNm	mNm
280	360	19,6	8,1
300	390	24,2	10,1
320	415	30,7	12,3
350	450	39,7	15,9
400	525	59,6	22,9
450	590	77,9	30
500	655	97,8	37,6

Testing method / Metod Testiranja	Standard	Tolerances / Tolerancija
Brightness / Belina	ISO 2470	80±1%
Grammage / Gramatura	ISO 536	±2%
Thickness / Debljina	ISO 534	±5%
Stiffness / Krutost	DIN 53122	-15%
Testing climate		23 ± 1 ⁰ C 50 ± 2% RH

**Recommended printing methods / Preporučeni metodi štampe: Offset, Flexo / Ofset štampa
, Flexo štampa**

Valid from 03/2015

Umka DOO Beograd, 13. Oktobra 1,11260 Umka

Tel: +381 11 36 02 600, Fax: +381 11 8026 995

Email: sales@umka.rs web: www.umka.rs

All figures mentioned above may be subject to technical changes.