

Tehnička specifikacija
Technical specification

Grammage Gramatura	Thickness Debljina	Stiffness <i>Krutost</i> LW5°		Stiffness <i>Krutost</i> TABER 15°	
		md	cd	md	cd
<i>g/m²</i>	<i>µm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>
230	285	8,2	4	4,1	2
250	315	13,5	5,7	6,8	2,9
280	360	19,6	8,1	9,8	4,1
300	390	24,2	10,1	12,1	5,1
320	415	30,7	12,3	15,4	6,2
350	450	39,7	15,9	18,9	7,6
380	495	51,8	20,1	24,7	9,6
400	525	59,6	22,9	28,4	10,9
450	590	77,9	30	37,1	14,3

*L&W figures are binding, Taber figures are indicative

*L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni

Umka Color - GD2

Testing Metod <i>Metod Testiranja</i>	Standard <i>Standard</i>	Tolerances <i>Tolerancija</i>
 <i>Belina</i> Brightness	ISO2470	80±1%
 <i>Gramatura</i> Grammage	ISO536	±2%
 <i>Debljina</i> Thickness	ISO534	±5%
 <i>Krutost</i> Stiffness	DIN53121	-15%
 <i>Klima za ispitivanje</i> Testing climate		23±°C 50±2%°RH
 <i>Reciklabilnost</i> Recyclability	EN13430	in terms of the norm
 <i>Biorazgradljivost</i> Biodegradability	EN13432	in terms of the norm

Recommened printing methods
Preporučeni metod štampe

Offset, Flexo
Ofset štampa, Flexo štampa
valid from 01.01.2020