

Tehnička specifikacija
Technical specification

Grammage Gramatura	Thickness Debljina	Stiffness <i>Krutost</i> LW5° md	Stiffness <i>Krutost</i> LW5° cd	Stiffness <i>Krutost</i> TABER 15° md	Stiffness <i>Krutost</i> TABER 15° cd
<i>g/m²</i>	<i>μm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>
230	280	8	4	4	2
250	310	12,7	5	6,4	2,5
280	355	18,4	7,4	9,2	3,7
300	385	22,4	9,5	11,2	4,8
320	410	27,9	11,4	14	5,7
350	445	35,9	14,4	17,1	6,9
400	520	51,7	20,3	24,6	9,7
450	585	70,3	30	33,5	14,3

L&W figures are binding, Taber figures are indicative

*L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni

Umka Pak - GD3

	Testing Metod Metod Testiranja	Standard Standard	Tolerances Tolerancija
	Belina Brightness	ISO2470	77±1%
	Gramatura Grammage	ISO536	±2%
	Debljina Thickness	ISO534	±5%
	Krutost Stiffness	DIN53121	-15%
	Klima za ispitivanje Testing climate		23±1°C 50±2%°RH
	Reciklabilnost Recyclability	EN13430	in terms of the norm
	Biorazgradljivost Biodegradability	EN13432	in terms of the norm

Recommened printing methods

Preporučeni metod štampe

Offset, Flexo

Ofset štampa, Flexo štampa

valid from 01.01.2020