

Tehnička specifikacija Technical specification

Grammage Gramatura	Thickness Debljina	Stiffness <i>Krutost</i> LW5° md	Stiffness <i>Krutost</i> TABER 15° cd	Stiffness <i>Krutost</i> TABER 15° md	Stiffness <i>Krutost</i> TABER 15° cd
g/m^2	μm	mNm	mNm	mNm	mNm
280	360	19,6	8,1	9,8	4,1
300	390	24,2	10,1	12,1	5,1
320	415	30,7	12,3	15,4	6,2
350	450	39,7	15,9	18,9	7,6
400	525	59,6	22,9	28,4	10,9
450	590	77,9	30	37,1	14,3

*L&W figures are binding, Taber figures are indicative

*L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni

Testing Metod <i>Metod Testiranja</i>	Standard Standard	Tolerances <i>Tolerancija</i>
 Belina Brightness	ISO2470	80±1%
 Gramatura Grammage	ISO536	±2%
 Debljina Thickness	ISO534	±5%
 <i>Krutost</i> Stiffness	DIN53121	-15%
 Klima za ispitivanje Testing climate		23±1°C 50±2%°RH
 <i>Reciklabilnost</i> Recyclability	EN13430	in terms of the norm
 Biorazgradljivost Biodegradability	EN13432	in terms of the norm

Recommened printing methods
Preporučeni metod štampe

Offset, Flexo

Ofset štampa, Flexo štampa

valid from 01.01.2020