








## Tehnička specifikacija Technical specification

Grammage Gramatura	Thickness Debljina	Stiffness <i>Krutost</i> LW5°		Stiffness <i>Krutost</i> TABER 15°	
		md	cd	md	cd
$g/m^2$	$\mu m$	$mNm$	$mNm$	$mNm$	$mNm$
300	390	24,2	10,1	12,1	5,1
320	415	30,7	12,3	15,4	6,2
350	450	39,7	15,9	18,9	7,6
380	495	51,8	20,1	24,7	9,6
400	525	59,6	22,9	28,4	10,9
450	590	77,9	30	37,1	14,3

\*L&W figures are binding, Taber figures are indicative

\*L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni

# Umka Brown Back

	Testing Metod Metod Testiranja	Standard Standard	Tolerances Tolerancija
 <b>Brightness</b>	Belina	ISO2470	80±1%
 <b>Grammage</b>	Gramatura	ISO536	±2%
 <b>Thickness</b>	Debljina	ISO534	±5%
 <b>Stiffness</b>	<i>Krutost</i>	DIN53121	-15%
 <b>Testing climate</b>	Klima za ispitivanje		23±°C 50±2%°RH
 <b>Recyclability</b>	Reciklabilnost	EN13430	in terms of the norm
 <b>Biodegradability</b>	Biorazgradljivost	EN13432	in terms of the norm

Recommended printing methods  
Preporučeni metod štampe

**Offset, Flexo**

Ofset štampa, Flexo štampa

Valid from 1.4.2023.