

Tehnička specifikacija Technical specification

Grammage Gramatura	Thickness Debljina	Stiffness Krutost md	LW5° cd	Stiffness Krutost md	TABER 15° cd
<i>g/m²</i>	<i>μm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>
300	390	24,2	10,1	12,1	5,1
320	415	30,7	12,3	15,4	6,2
350	450	39,7	15,9	18,9	7,6
380	495	51,8	20,1	24,7	9,6
400	525	59,6	22,9	28,4	10,9
435	567	73	28	33,2	12,8
450	590	77,9	30	37,1	14,3

**L&W figures are binding, Taber figures are indicative*
**L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni*

Testing Metod Metod Testiranja	Standard Standard	Tolerances Tolerancija
 Brightness Belina	ISO2470	80±1%
 Grammage Gramatura	ISO536	±2%
 Thickness Debljina	ISO534	±5%
 Stiffness Krutost	DIN53121	-15%
 Testing climate Klima za ispitivanje		23±1°C 50±2%°RH
 Recyclability Reciklabilnost	EN13430	in terms of the norm
 Biodegradability Biorazgradivost	EN13432	in terms of the norm

Recommended printing methods
 Preporučeni metod štampe

Offset, Flexo
 Ofset štampa, Flexo štampa