

Tehnička specifikacija Technical specification

Grammage Gramatura	Thickness Debljina	Stiffness Krutost md	LW5° cd	Stiffness Krutost md	TABER 15° cd
<i>g/m²</i>	<i>μm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>
230	285	8,2	4	4,1	2
250	315	13,5	5,7	6,8	2,9
280	360	19,6	8,1	9,8	4,1
300	390	24,2	10,1	12,1	5,1
320	415	30,7	12,3	15,4	6,2
350	450	39,7	15,9	18,9	7,6
380	495	51,8	20,1	24,7	9,6
400	525	59,6	22,9	28,4	10,9
450	590	77,9	30	37,1	14,3

**L&W figures are binding, Taber figures are indicative*
**L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni*

Umka Color - GD2

Testing Metod Metod Testiranja	Standard Standard	Tolerances Tolerancija
 Brightness Belina	ISO2470	80±1%
 Grammage Gramatura	ISO536	±2%
 Thickness Debljina	ISO534	±5%
 Stiffness Krutost	DIN53121	-15%
 Testing climate Klima za ispitivanje		23±1°C 50±2%°RH
 Recyclability Reciklabilnost	EN13430	in terms of the norm
 Biodegradability Biorazgradivost	EN13432	in terms of the norm

Recommended printing methods
Preporučeni metod štampe

Offset, Flexo
Ofset štampa, Flexo štampa