

Tehnička specifikacija Technical specification

Grammage Gramatura	Thickness Debljina	Stiffness Krutost md	LW5° cd	Stiffness Krutost md	TABER 15° cd
<i>g/m²</i>	<i>μm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>	<i>mNm</i>
230	280	8	4	4	2
250	310	12,7	5	6,4	2,5
280	355	18,4	7,4	9,2	3,7
300	385	22,4	9,5	11,2	4,8
320	410	27,9	11,4	14	5,7
350	445	35,9	14,4	17,1	6,9
380	490	43,6	17,3	20,1	8,2
400	520	51,7	20,3	24,6	9,7
450	585	70,3	27	33,5	14,3

**L&W figures are binding, Taber figures are indicative*
**L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni*

Umka Pak - GD3

Testing Metod Metod Testiranja	Standard Standard	Tolerances Tolerancija
 Brightness Belina	ISO2470	77±1%
 Grammage Gramatura	ISO536	±2%
 Thickness Debljina	ISO534	±5%
 Stiffness Krutost	DIN53121	-15%
 Testing climate Klima za ispitivanje		23±1°C 50±2%°RH
 Recyclability Reciklabilnost	EN13430	in terms of the norm
 Biodegradability Biorazgradivost	EN13432	in terms of the norm

Recommended printing methods **Offset, Flexo**
 Preporučeni metod štampe Ofset štampa, Flexo štampa