

## Tehnička specifikacija Technical specification

| Grammage<br>Gramatura                                                                                                       | Thickness<br>Debljina | Stiffness<br>Krutost md | LW5°<br>cd | Stiffness<br>Krutost md | TABER 15°<br>cd |
|-----------------------------------------------------------------------------------------------------------------------------|-----------------------|-------------------------|------------|-------------------------|-----------------|
| $g/m^2$                                                                                                                     | $\mu m$               | $mNm$                   | $mNm$      | $mNm$                   | $mNm$           |
| 280                                                                                                                         | 360                   | 19,6                    | 8,1        | 9,8                     | 4,1             |
| 300                                                                                                                         | 390                   | 24,2                    | 10,1       | 12,1                    | 5,1             |
| 320                                                                                                                         | 415                   | 30,7                    | 12,3       | 15,4                    | 6,2             |
| 350                                                                                                                         | 450                   | 39,7                    | 15,9       | 18,9                    | 7,6             |
| 400                                                                                                                         | 525                   | 59,6                    | 22,9       | 28,4                    | 10,9            |
| 450                                                                                                                         | 590                   | 77,9                    | 30         | 37,1                    | 14,3            |
| *L&W figures are binding, Taber figures are indicative<br>*L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni |                       |                         |            |                         |                 |

## Umka Special - GT2

| Testing Metod<br>Metod Testiranja                                                                                                  | Standard<br>Standard | Tolerances<br>Tolerancija |
|------------------------------------------------------------------------------------------------------------------------------------|----------------------|---------------------------|
|  <b>Brightness</b><br>Belina                    | ISO2470              | 80±1%                     |
|  <b>Grammage</b><br>Gramatura                   | ISO536               | ±2%                       |
|  <b>Thickness</b><br>Debljina                   | ISO534               | ±5%                       |
|  <b>Stiffness</b><br>Krutost                    | DIN53121             | -15%                      |
|  <b>Testing climate</b><br>Klima za ispitivanje |                      | 23±1°C<br>50±2%°RH        |
|  <b>Recyclability</b><br>Reciklabilnost        | EN13430              | in terms of the norm      |
|  <b>Biodegradability</b><br>Biorazgradivost   | EN13432              | in terms of the norm      |

**Recommended printing methods**  
 Preporučeni metod štampe

**Offset, Flexo**  
 Ofset štampa, Flexo štampa