

Tehnička specifikacija Technical specification

Grammage Gramatura	Thickness Debljina	Burst Strength Snaga Pritiska	SCT° Kompresija	Brightness Belina
g/m^2	μm	kPa	kN/m	%
180	205	360	2,6	80
210	245	400	2,9	80

Testing Metod Metod Testiranja	Standard Standard	Tolerances Tolerancija
 Brightness Belina	ISO2470	±1%
 Grammage Gramatura	ISO536	±2%
 Thickness Debljina	ISO534	±5%
 Burst strength Snaga pritiska	ISO2759	-10%
 SCT Kompresija	ISO9895	-0.3%
 Testing climate Klima za ispitivanje		23±1°C 50±2%°RH
 Recyclability Reciklabilnost	EN13430	in terms of the norm
 Biodegradability Biorazgradivost	EN13432	in terms of the norm

Recommended printing methods
 Preporučeni metod štampe

Offset, Flexo
 Ofset štampa, Flexo štampa